

SeaRox® SL 660

SeaRox SL 660 is a slab made of stone wool. The product is specially developed to provide maximum fire protection. SeaRox SL 660 can be supplied with reinforced aluminium foil.



Application


SeaRox SL 660 is used for hydrocarbon fire protection of steel bulkheads, decks and firewalls. Suitable also for use as infill insulation in A and B class doors and panels.

Product properties

Properties	Performance				Norm
Thermal conductivity	T (°C) λ (W/mK)	10 0,037	100 0,046	300 0,077	EN 12667
Nominal density	150 kg/m³				EN 1602 / IMO
Compressive strength	-				EN 826
Fire classification	Non-combustible Approved for H class steel constructions Low Flame-Spread Properties (for facings)				Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m²				EN 1609 AC
Max. Application Temperature	Wool: 680°C Facing: 80°C				-
Sound absorption directly mounted	α _w = 0,90 Thickness: 2x50 mm				EN 14706
Facings (on request)	Reinforced alu foil				IMO A.653(16) (low flame - spread)

Compliance

- SeaRox SL 660 complies to directive 2014/90/EU of 23 July on marine equipment (MED) and IMO 2010 FTP Code.
- Above product declarations are also applicable for product with optional facing.
- ROCKWOOL stone wool insulation is made from volcanic rock and complies with Note Q, regulation (EC) No. 1272/2008.



0575



0097

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.